| COMMON NAME | MANCHICHE |
|-----------------------|---|
| SCIENTIFIC NAME | Lonchocarpus castilloi |
| COLOR | Coffee with reddish coffee |
| BASIC SPECIFIC WEIGHT | 0.70 gr / cm3 |
| TEXTURE | Fine to Medium |
| THREAD | Interlocked |
| VETEATED | Exotic figure |
| WORKABILITY | Medium to difficult |
| NATURAL RESISTANCE | Medium |
| SAWED | Medium to difficult |
| DURABILITY | High |
| STATIC FLEXION | 12% humidity |
| BREAK MODULE | (kg / cm2) 1468-1784 |
| ELASTICITY MODULE | (kg / cm2) 171,306-214,132 |
| COMPRESSION | 12% humidity |
| PARALLEL | (kg / cm2) 836-907 |
| JANKA HARDNESS | 12% humidity |
| USES | Interior and exterior floors, structures for construction in general, decks and moldings. |

