



CHICHIPATE

Scientific Name: *Sweetia panamensis*

Color: Heartwood is brown or olive green; sapwood is well-defined, yellowish cream with golden highlights

Basic Specific Gravity: 0.80 g/cm³

Figure: Attractive, wavy

Workability: Moderately difficult

Natural Resistance: Moderate to high

Compression: 12% moisture

Janka Hardness: 12% moisture

Uses: Construction, flooring, posts, sawn timber, utensils.