



MANCHICHE

Scientific Name: Lonchocarpus castilloi

Color: Brown to reddish brown

Basic Specific Gravity: 0.70 g/cm³

Texture: Fine to medium

Grain: Interlocked

Figure: Attractive

Workability: Medium to difficult

Natural Resistance: Medium

Sawing: Medium to difficult

Durability: High

Static Bending: 12% moisture

Modulus of Rupture: 1468–1784 kg/cm²

Modulus of Elasticity: 171,306-214,132 kg/cm²

Compression: 12% moisture

Parallel: 836-907 kg/cm²

Janka Hardness: 12% moisture

Uses: Indoor and outdoor flooring, general

construction structures, decks, and moldings.